

Rubiomonocoat EXTERIOR MAINTENANCE OIL

DESCRIPTION:

RMC Exterior Maintenance Oil is a revitalising oil which for the maintenance of external wooden surfaces which have been treated with the Rubio Monocoat Exterior wood protection product of your choice. Add the **RMC Sunprimer Color** in the colour of your original choice.

It is essential to carry out this treatment at least once per year to guarantee optimum protection for your wood.

SPECIAL PROPERTIES:

Since wood is a living material and therefore subject to shrinkage and expansion, microscopic hairline cracks will occur after some time. This is especially the case for decking that has been standing under pools of water, snow, or suffered the effects of UV rays and wear through walking on it. Maintenance with **RMC Exterior Maintenance Oil** will reprotect these hairline cracks.

DIRECTIONS FOR USE:

1. Preparation: clean carefully with clean water. Allow the surface to dry completely before starting the treatment.
2. Pour the **RMC Sunprimer Color** of the initial treatment into a clean container. Add the **RMC Exterior Maintenance Oil**. (Respect the correct mixing quantities - see below) Mix both products thoroughly.
3. Apply the mixed liquid with the RMC 220 X 32 brush, a graining brush or a sponge. Do not apply in direct sunlight.
4. Allow to react for 10 to 15 min. Wipe off any excess product with a fluff-free cloth.
5. Drying time: 6 to 8 hours. The surface may be walked on after 8 to 12 hours.

Clean all brushes and other tools used with **RMC Biocleaner**.

FREQUENCY:

- Initial application: preferably within 5 -6 months after application of RMC Decking Oil Duo System.
- Subsequent applications: 1 x per year.

MIXTURE RATIO

RMC Exterior Maintenance Oil is available in:

a) 1 litre and 5 litre cans

To prepare a large quantity of the product, use a large capacity spray, taking account of the proportions:

400 ml **RMC Exterior Maintenance Oil**/ 100 ml **RMC Sunprimer Color**.
1 litre **RMC Exterior Maintenance Oil**/ 200 ml **RMC Sunprimer Color**.
5 litres **RMC Exterior Maintenance Oil**/ 1000 ml (1L) **RMC Sunprimer**

Color.

b) Ecospray (Consult the TDS)

Refill: pour 400 ml **RMC Exterior Maintenance Oil** into the spray, and add 100 ml **RMC Sunprimer Color** in the colour of original treatment. Shake vigorously before use.

Effective action of the product can only be guaranteed if these ratios are observed. Before each refilling or use of the product, stir the mixture thoroughly.

USAGE:

30 to 50 m² per liter.

These usages are merely indicative. Results depend on wood type and method of preparation. It is always recommended to make a sample in order to calculate the exact usage.

TECHNICAL SPECIFICATIONS:

Oil

pH: +/- 8

Specific weight: +/- 0.90

Colour: opaque

Fragrance: specific

PACKAGING:

1L - 5L can.

STORAGE:

The product can be stored for up to 12 months. It must be stored in dry conditions and in the original packaging. Protect from frost.

CAUTION:

The product may NOT be diluted!
Cloths, saturated with oil, may spontaneously combust.
After usage, they need to be soaked in water before disposal.

DISCLAIMER: It is the responsibility of the user to determine through own testing whether the product is suited for its chosen application. Muylle Facon NV is not liable for any resultant damage. The above information may be subject to amendments, which will be published in revised versions of the technical sheet. We waive all responsibility for unsatisfactory results that are due to causes unrelated to the quality of the product. This technical information has been collected on the basis of current information and knowledge. The most recent technical sheets can be requested or are available on the website.

PROVIDED BY:



Consult the safety sheet before use.

Date TDS: 03/05/12

MUYLLE  **FACON**

MADE IN BELGIUM by **N.V. MUYLLE - FACON S.A.**
Ambachtenstraat 58 - B-8870 Izegem (Industriezone Abele)
Tel. +32 (0)51 30 80 54 - Fax + 32 (0)51 30 99 78 - HRK 1823
info@muyllefacon.be - www.rubiomonocoat.com

